

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) EP 0 921 105 A1

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication: 09.06.1999 Bulletin 1999/23

(51) Int Cl.6: C03C 8/02

(21) Application number: 98204021.4

(22) Date of filing: 28.11.1998

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU

MC NL PT SE

Designated Extension States: **AL LT LV MK RO SI**

(30) Priority: 02.12.1997 ES 9702506

(71) Applicant: Esmaltes, S.A.
12110 Alcora (Castellon) (ES)

(72) Inventor: Bakali Bakali, Jorge 12110 Alçora (Castellon) (ES)

(74) Representative: Ungria Lopez, Javier et al Avda. Ramon y Cajal, 78
28043 Madrid (ES)

(54) Bactericidal ceramic enamel and uses thereof

(57) The ceramic enamel is characterized in that it includes in its composition a rare earth oxide (CeO₂) along with conventional silicon, aluminum, calcium oxides, etc. Said composition permits the existence of

electronic transfers capable of affecting oxidation-reduction processes of live matter that are converted into the bactericidal capacity thereof.

The enamel is useful in the ceramic sector.




FIG. 1

20

TECHNICAL FIELD OF THE INVENTION

[0001] The present invention fits in the technical field of ceramic enamels for wall and floor coverings and the like, such as wall tiles, floor tiles, sanitary elements (sinks, bath tubs, all ceramic complements of a bathroom, etc.), etc.

1

[0002] More specifically, the present invention provides a new type of bactericidal ceramic enamels.

PRIOR ART OF THE INVENTION

[0003] The Japanese firm Toto has developed a tile that has a photocatalytic layer of titanium dioxide enamel finished with a copper and silver compound. When this photocatalytic layer absorbs light, it activates the metal ions, that kill the bacteria that come in contact with the ceramic tile.

[0004] However, these tiles have variations in their tonality and effectiveness in the passing of time.

DETAILED DESCRIPTION

[0005] The present invention, as indicated in its title, refers to some new bactericidal ceramic enamels.

[0006] The applicant has developed a new type of ceramic enamels, unconventional up to now in the ceramic sector, that combine the development of highly desirable optical properties, such as for example, a high refraction index (lustrous material) with a bactericidal action.

[0007] Furthermore, the developed material is provided with high quality performance qualities, since it does not eventually undergo any variation of tonality or wear, as in the case of this type of product of the prior art.

[0008] The ceramic enamel of the present invention is characterized in that its composition includes rare earth oxides. This makes it a material capable of electronic transfers inside of it produced by a light-matter interaction. These electronic transfers may be capable of causing a redox process on the live matter (for example, bacteria) eventually deposited on or in close contact with the enameled surface, exercising with it a bactericidal action.

[0009] The material of the present invention is characterized in that it has the following composition:

Oxide	Percentage (% by weight)
SiO ₂	35-55
Al ₂ O ₃	5-15
BaO	0-5
B ₂ O ₃	0-10
CaO	5-10
CeO ₂	2-10

(continued)

Oxide	Percentage (% by weight)
ZnO	5-10
K ₂ O	0-5
Na ₂ O	0-5
ZrO ₂	0-5

[0010] The ceramic enamel of the invention is obtained by fritting or by mixing. A combination of frits and/or formulations with these characteristics has been developed within this range of composition. Each one of these enamels is applied on the tile as a base enamel, serigraphy and/or sprayed and it is baked in an industrial furnace.

[0011] The absorption properties of the material of the invention have been determined by ultraviolet visible spectrophotometry using a wave length range between 800 and 200 nm (namometers).

[0012] A wide band in the range of 400 to 200 nm (ultraviolet range), which is assigned to electronic charge energy transitions, or the passing of electrons of one energy level to another, is observed in the absorption spectrum of the material of the invention. This electronic charge transfer tends to be normally produced between the fundamental level and a higher level and is associated with the light absorption in the wave lengths corresponding to the area of the next ultraviolet spectrum and the visible one.

[0013] Figure 1 shows the electronic transfer in solids that affect the optical properties, indicating the energy levels for two atoms, A and B, together with some electronic states characteristic of solids.

[0014] Likewise, emission studies of the enamels of the invention have been carried out to characterize specific properties. The excitation and emission spectrums of the developed bactericidal material have been studied. The maximums of the excitation and emission spectrums are between wave lengths of 270 and 400 nm.

[0015] Likewise, the tiles coated with the enamel of the invention have been subjected to luster tests, using a Multi-Gross 268 luster gage, that measures the light reflected photoelectrically at a 200 angle, obtaining lusters in the range of 88-99 GU (GU gross units, luster units).

[0016] The studies regarding the bactericidal activity thereof have been carried out in specialized microbiology laboratories, obtaining very satisfactory results since at bacterial concentrations similar to those that may exist on the walls, there has not been any bacterial grown on the tiles coated with the enamels of the invention.

[0017] Furthermore, studies of the effect that the intensity and the type of lighting may have on the bactericidal effect have been carried out.

BRIEF DESCRIPTION OF THE FIGURE

[0018] Sole figure 1 is an illustration of the way in which electronic transfers are produced in solids in general. The numerical references that appear in the same have the following meaning:

- 1.- Conduction band promotion
- 2.- Differences between bands (GAP).
- 3.- Exciting transfers d-d, f-f
- 4.- Valence band promotion
- 5. Charge transfer

EMBODIMENTS OF THE INVLENTION

[0019] A ceramic enamel is prepared by mixing, or obtaining a frit, from a composition that is found within the previously stated composition range. The composition range is given to adjust the material to the baking temperature in each case, due to the fact that enamels to be applied in rapid double baking cycle, in porous single baking and in stoneware single baking, have been developed.

[0020] Said frit is ground and applied as a base enamel, serigraphy and/or sprayed on the engobe and/or enameled carrier (enameled, when it is not applied as a base enamel). It is baked in an industrial furnace at the temperature and for the time characteristic of the type of ceramic carrier used, that tends to vary between 1120-1200 C and 40-80 min. for stoneware, 1100-1170 C and 30-70 min. for porous carrier and 1000-1120 C and 25-60 min. for rapid cycle.

ABSORBENCY SPECTRUM

[0021] Band width from 400 to 200 nm. Determined with a PERKIN-ELMER, UV/VIS LAMBDA 19 model, spectrophotometer, applying the diffuse solid reflectance method.

LUSTER INDEX

[0022] 88-99 GU luster measured with a Multi-Gross 268 luster gage, with a 20^o measuring angle.

MICROBIOLOGICAL TESTS

[0023] After baking, the tiles are cut into 5 x 5 cm pieces and taken to the microbiology laboratory where they are sterilized first of all in an autoclave.

[0024] Afterwards, each tile is placed on a Petri dish and painted with a standard solution of Staphylococcus aureus at different turbidities (0.001 and 0.002 Mac Farlan turbidity). The control tiles, in other words, tiles that do not have bactericidal enamel, are also tested.

[0025] The tests are quadrupled in all cases, using four tiles with bactericidal treatment and four others without treatment.

[0026] After 12 hours of planting and being exposed to the light of 36 watt fluorescent tubes, the tiles are placed with the enameled surface in contact with sterile chocolate agar, in Petri dishes. The tile is left there for one more hour, to give time for all the live bacteria contained in the tiles to pass to the agar, where they grow.

[0027] After this experiment, bacterial growth is tested. Such grown is very scarce and non-existent in the tiles enameled with the product of the invention, while there is growth on the tiles there the material of the invention was not contained.

Claims

15

35

45

50

55

1. Bactericidal ceramic enamel, characterized in that it has the following composition:

Oxide	Percentage (% by weight)
SiO ₂	35-55
Al ₂ O ₃	5-15
BaO	0-5
B ₂ O ₃	0-10
CaO	5-10
CeO ₂	2-10
ZnO	5-10
K ₂ O	0-5
Na ₂ O	0-5
ZrO ₂	0-5

- **2.** Enamel, according to claim 1, characterized in that it is obtained by mixing or by fritting.
- 3. Use of the ceramic enamel of claims 1 and 2, in the manufacture of bactericidal ceramic coverings for floors and walls.

3




FIG. 1



EUROPEAN SEARCH REPORT

Application Number EP 98 20 4021

		ERED TO BE RELEVANT		
Category	Citation of document with in of relevant pass	ndication, where appropriate, ages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.6)
A	PATENT ABSTRACTS OF vol. 096, no. 008, & JP 08 100274 A (LTD), 16 April 1996 * abstract *	30 August 1996 TAKARA STANDARD CO	1-3	C03C8/02
4	EP 0 653 161 A (SUM LTD) 17 May 1995 * claims *	ITOMO OSAKA CEMENT CO	1-3	
4	EP 0 684 075 A (TOT) * abstract *	 O LTD) 29 November 199 	5 1-3	
				TECHNICAL FIELDS SEARCHED (Int.Cl.6)
				C03C
	The present search report has I			
	Place of search	Date of completion of the search		Examiner
	THE HAGUE	9 March 1999	Van	Bommel, L
X : part Y : part doct A : tech O : non	ATEGORY OF CITED DOCUMENTS icularly relevant if taken alone icularly relevant if combined with anot ument of the same category inclogical background its written disclosure rmediate document	E : earlier patent after the filing her D : document cite L : document cite	d in the application d for other reasons	ished on, cr

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 98 20 4021

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

09-03-1999

	Publication date	Patent family member(s)		Publication date
EP 0653161 A	17-05-1995	JP 6340513 JP 7101791 JP 7291658 DE 69408096 DE 69408096 DE 653161 WO 9427442 US 5807641	A B A B D B T B T	13-12-19 18-04-19 07-11-19 26-02-19 10-06-19 04-01-19 08-12-19 15-09-19
EP 0684075 A	29-11-1995	JP 7155598 JP 7191011 JP 7232080 JP 8103488 JP 8108075 JP 8131524 JP 8131834 JP 8131842 JP 8131842 AU 1199895 US 5853866 CA 2155822 CN 1120819 WO 9515816 JP 8066635 JP 7222928 JP 8150197 AU 678330 AU 1199595 JP 8224481	A A A A A A A A A A A B A B A	20-06-19 28-07-19 05-09-19 23-04-19 30-04-19 14-05-19 28-05-19 28-05-19 28-05-19 27-06-19 15-06-19 17-04-19 12-03-19 22-08-19 22-05-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19 23-06-19